

UNIPLEX FRP-64

Poly(2,6-Dibromophenylene oxide)

CAS No. 69882-11-7

Description: A off-white melt-processable solid flame retardant containing 64% aromatic bromine. Resin systems compounded with Uniplex FRP-64 have high chemical and flame resistance, minimal thermal discoloration, and excellent light stability.

Applications: Unfilled and Reinforced Thermoplastic Polyester (PBT and PET)
Unfilled and Reinforced Polyamide Resins (Nylon 6 and 66)

Typical Properties:

Bromine Content (%) 64 min.
Thermal Stability (5% Loss) 400°C
Iron Content (ppm, AA) 2 max.

Solubility (g/100g Solvent at 25°C):

Water Insoluble
Acetone Insoluble
Isopropanol Insoluble
Xylene Partially soluble
Tetrahydrofuran >40

General Specifications:

Appearance Off-white powder
Softening Range (DSC) 210-240°C
Sodium Bromide Content (%) 0.10 max.
Tribromophenol Content (% by GC) 0.15 max.
Loss on Drying (2 hr, 135°C) 1.0 max.

Health & Safety: Refer to Material Safety Data Sheet (MSDS).

Uniplex FRP-64		Date Issued: 6/18/09
www.unitexchemical.com	Page 1 of 2	Supersedes: 10/12/04

Application Data: Polyester (PBT and PET) and Polyamide (Nylon 6 and Nylon 66) compounds incorporating Uniplex FRP-64 demonstrate excellent mechanical and thermal stability properties. Since Uniplex FRP-64 is a polymeric flame retardant, it does not bloom or migrate from the plastic or cause plate-out during injection molding. Uniplex FRP-64 melt blends during normal processing conditions to produce good flow characteristics necessary for thin walled or multi-cavity parts. This flame retardant is particularly useful in the manufacture of electrical/electronic component parts (e.g. electrical connectors)

Flame retardant Polyester Resins:

Compound Type	Loading FRP-64,%	Loading Sb ₂ O ₃ ,%	UL-94 Rating 1/16 in	HDT (264 psi, °C)
Unreinforced PBT	20	5	V-0	66
30% Glass-filled PBT	14	3.5	V-0	203
30% Glass-filled PET	10	2.5	V-0	201

Flame retardant Polyamide Resins:

Compound Type	Loading FRP-64,%	Loading Sb ₂ O ₃ ,%	UL-94 Rating 1/16 in	HDT (264 psi, °C)
Unreinforced Nylon 6	18	4.5	V-0	65
Unreinforced Nylon 66	18	4.5	V-0	72
20% Glass-filled Nylon 66	16	4	V-0	233

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale. Suggestions for uses of our product should not be understood as recommendations that they be used in violation of any patents.

Uniplex FRP-64		Date Issued: 6/18/09
www.unitexchemical.com	Page 2 of 2	Supersedes: 10/12/04