

UNIPLEX M8M

Melamine Molybdate

CAS RN 65235-34-9

Description: A fire and smoke suppressant additive for flexible and rigid PVC compounds. This product may be also useful in a number of different polyolefin and polyamide applications as a synergist with melamine-based non-halogen flame retardants.

Applications:
Rigid and Flexible PVC compounds
Flexible halogenated alloys (e.g. PVC/PVDF)
Non-halogen Polyolefinic compounds
Non-halogen glass-filled Nylon compounds

Typical Properties:
Molybdenum Content (%) 45 min.
Thermal Stability (5% Loss) >300°C

Solubility (g/100g Solvent at 25°C):
Water Insoluble
Acetone Insoluble
Isopropanol Insoluble
Xylene Insoluble
Tetrahydrofuran Insoluble

General Specifications:
Appearance Off-white Powder
Particle Size, D_{97} , Laser Diffraction 5 microns max.
pH, 5 % in Water 5 - 8
Loss on Drying (2 hr, 135°C) 0.5 max.

Health & Safety: Refer to Material Safety Data Sheet (MSDS).

Application Data:
This product is useful in both rigid and flexible formulations of halogenated vinyl resins as a replacement for Ammonium octamolybdate as a smoke suppressant. Increased oxygen indices are also found indicating improved flame resistance.

Uniplex M8M was compounded into rigid PVC at 200°C with Geon 30 PVC, 2 phr Microthene 510 Lubricant, 2 phr Tin Thioglycolate Stabilizer and 2 phr Uniplex M8M. The compound was compression molded and subjected to various tests with the results tabulated in Table 1.

Uniplex M8M www.unitexchemical.com	Page 1 of 2	Date Issued: 6/18/09 Supersedes: 12/15/00
---------------------------------------	-------------	--

TABLE 1 RIGID PVC COMPOUNDS

Example	Loading (phr) Molybdenum compound	Thermal Stability (5% Loss TGA)	Comound Thermal Stability (min)	Oxygen Index	%Smoke Reduction (Dmc in ASTM E-662)
Control	None	---	>120	45	----
Uniplex M8M	2	380°C	>120	49	87

Flexible PVC(Geon 30) compounds were prepared by dry blending additives with Geon 30 PVC and then compounding in a two roll mill at 160°C. The compounds were compression molded and tested. The results are tabulated in Table 2. The general purpose formula used was:

MATERIAL	LOADING (phr)
Geon 30 PVC	100
Uniplex 546-A	34
Uniplex FRP-45	40
Molybdate complex	2.5
Antimony Trioxide	2
Lead Stabilizer (Dythal XL)	7

TABLE 2 FLEXIBLE PVC COMPOUNDS

Example	Loading (phr) Molybdenum compound	Thermal Stability (5% Loss TGA)	Compound Thermal Stability (min)	Oxygen Index	%Smoke Reduction (Dmc in ASTM E-662)
Control	None	---	>120	34	----
AOM	5	290°C	>120	39	30
Uniplex M8M	5	380°C	>120	41	35

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale. Suggestions for uses of our product should not be understood as recommendations that they be used in violation of any patents.